

CCS™ QUIKPRIME™

COATING – STRUCTURAL EPOXY ADHESIVE PRIMER FOR POLYMER COATING & FLOORING SYSTEMS

TECHNICAL DATA SHEET FOR PROFESSIONAL CONTRACTOR USE ONLY

DESCRIPTION

CCS™ QuikPrime™ is a 2:1 mix ratio, two-component, solvent-free, low viscosity, structural epoxy adhesive primer designed to prime properly prepared concrete or steel. It is one of the few primers that meets ASTM C881, Type IV, Class B and Class C. It can be applied over fresh concrete (24 hours after placement 73°F (23°C), hardened concrete, and steel. It is an ideal primer for polymer products, such as: epoxies, polyaspartics, polyureas, and polyurethanes. It can be applied over properly prepared concrete substrates that are dry, damp, wet, and free of standing water. Applications include priming properly prepared concrete and steel substrates when rebuilding damaged joint nosing, repairing spalled and deteriorated concrete, and sealing non-structural cracks in concrete. CCS™ QuikPrime™ can also be used as a prime coat in green concrete provided that the substrate can tolerate a negative side vapor barrier early in its cure cycle. The product's short cure cycle, tolerance of surface dampness, low viscosity, excellent adhesion in cold weather, and high bond strength to properly prepared surfaces make it ideally suited as a multipurpose primer. It contains no VOC's (volatile organic compounds).

- Meets - ASTM C881, Type I, II, IV and V, Grade 2, Class B and C and AASTHO M235, Type I, II, IV and V, Grade 2, Class B and C.

FEATURES

CCS™ QuikPrime™ is specifically formulated as a primer for bonding epoxies, polyaspartics, polyureas, and polyurethanes to dry, damp, and wet and concrete substrates that are free of standing water and steel substrates.

- Bonds to dry and damp substrates.
- High chemical resistance.
- Environmentally safe no VOC's.

TYPICAL USES

- A structural epoxy adhesive primer.
- Applied at temperatures as low as 35°F (1.7°C).
- Priming the substrates significantly improves the bond strength of the subsequently applied coatings, flooring, semi-rigid, and elastomeric control joint sealers and grouts, particularly to damp substrates.
- Can be placed as a primer over plastic (fresh) concrete 24 hours after placement.
- Is a convenient 2:1 (by vol.) mixing ratio
- A fast cure cycle for short downtimes.

COVERAGE RATE

Primer: Coverage 160 – 200 sq. ft. (14.9 – 18.6 sq. m.). ICRI – Guideline CSP 2 – 4. For more aggressive textures coverage may vary.

LIMITATIONS

The recommended minimum substrate temperature during installation and for cure is 35°F (1.7°C) and above.

- The maximum in-service temperature should be 20°F (-7°C) below the HDT (Heat Deflection Temperature) in bonding structural applications subjected to substantial and sustained shear stresses that may cause creep.

TECHNICAL DATA

7 days 73°F (23°C) unless otherwise indicated. Compressive strength of cement mortar 4,500 psi (13.0 MPa).

PHYSICAL PROPERTIES		TEST METHOD	VALUE
Mix Ratio by Volume			2:1
Mix Ratio by Weight			100:44
Color		Visual	Clear Amber
Weight per Gallon	Part A Part B Mixed	ASTM D1475	9.5 lbs. (5.2 kg) 8.3 lbs. (4.4 kg) 9.1 lbs. (4.9 kg)
Viscosity, CP	Part A Part B Mixed	ASTM D2393	300 150 250
Gel Time, 100 grams		ASTM D2471	15 Minutes
Primer Cure Time	50°F (10°C) 73°F (23°C) 90°F (32°C)	ASTM D7234	4 Hours 1.5 Hours 0.75 Hour
Tensile Strength		ASTM D638	9,180 psi (63.3 MPa)
Tensile Elongation		ASTM D638	2%
Bond Pull-Off Strength to Concrete		ASTM D7234	400 psi (2.8 MPa)
Hardness, Shore D		ASTM D2240	62
Heat Deflection Temperature		ASTM D648	135°F (57°C)

- When bonding plastic (fresh) concrete containing resinous admixtures, establish the suitability of the concrete mix before actual use.
- Do not add solvents or otherwise thin this product. Admixtures establish the suitability of the concrete mix before actual use.

PACKAGING

- Standard kit sizes of Part A + Part B: 3, 15, and 150 Gallon (11.36, 56.78 and 567.8 l.) kits. Available in cartridges.

SHELF LIFE

Three years minimum in unopened, original containers when stored between 50°F (10°C) and 90°F (32°C) in a dry place away from direct sunlight. Remixing of each component may be required upon prolonged storage.

CHEMICAL RESISTANCE

CCS™ QuikPrime™ has excellent resistance to a wide range of commonly encountered chemicals including acids and bases, aircraft and automotive fluids, petroleum fuels, cutting oils, etc. It has limited resistance to hydrocarbon solvents. Performance is a function of the specific chemical and concentration, ambient and solution temperatures, exposure times, and housekeeping procedures. For information on specific chemicals and exposure conditions, contact a ChemCo Systems Technical Representative

SURFACE PREPARATION

Substrate surfaces must be dry or damp, sound and free of all bond-inhibiting substances. Prepare surfaces in accordance with International Concrete Repair Institute, ICRI Guideline No. 310.215.6R Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, Polymer Overlays, and Concrete Repair, Concrete Surface Profile, CSP 2 to CSP 4. The concrete surfaces should have a minimum strength of 250 psi (1.72 MPa) in direct tension per ASTM C1583 Standard Test Method for Tensile Strength of Concrete Surfaces and the Bond Strength or Tensile Strength of Concrete Repair and Overlay Materials by Direct Tension (Pull-off Method). Steel surfaces should be cleaned to "white metal" according to SSPC-SP 5/NACE No. 1 White Metal Blast Cleaning is a standard used for white metal blast cleaning put forth by the SSPC (Society for Protective Coatings) and NACE (National Association of Chemical Engineers) international standard.

MIXING

CCS™ QuikPrime™ is a two-component adhesive. The resin to hardener (Part A : Part B) mix ratio is 2:1, by volume. Premix the individual components before drawing from bulk packaging. Wear safety glasses and clean neoprene rubber gloves when handling the material. Transfer the appropriate quantities of Part A and Part B into a mixing container. Use quantities that can be applied before the pot life of the material expires. Blend thoroughly using a Jiffy mixer blade attached to a low speed (350-750 rpm) electric or pneumatic drill. Proper mixing will take 2-3 minutes.

INSTALLING

Pour mixed material onto the prepared substrate and spread to the specified coverage with a V-notch trowel, squeegee, or paint roller. For large areas, spray application of the material is recommended. When mating two solid surfaces, apply a bonding agent to both surfaces. Allow all coated substrate surfaces to rest for 5-10 minutes before pouring fresh concrete or mating with another surface. In plastic to hardened concrete bonding applications, the bond line should be at least 15 mils. Lightweight concrete may require a second coat of epoxy adhesive. In other bonding applications, bond line thickness is less critical but should be at least 4 mils above the peaks of the surface profile. For additional application information, see ACI 503R, Chapter 7, Applying Epoxy Compounds.

RECOAT WINDOW

The recoat window is 24 hours when the substrate and ambient temperature are 75°F (24°C).

- Higher temperatures will shorten the recoat window and lower temperatures will lengthen the recoat window.
- During the interim between placement and recoating, job site conditions may result in contamination of the original surface, therefore acetone solvent wipe may be required.
- For heavier contamination, light screening or light sanding followed by removal of residue by vacuuming or acetone wipe (or both) may be required to remove the contamination
- The minimum time to recoat a 100% solid coating is when the product to be recoated is tack free.
- The recoat temperature is between 40°F (4°C) and 100°F (38°C).

Consult a ChemCo Systems Technical Representative for additional information.

AGGREGATE EXTENSION

One gallon of neat CCS™ QuikPrime™ yields 231 cubic inches, which can be extended with uniform sized sand that has been washed, kiln dried, and bagged.

- Add up to two gallons of aggregate to one gallon of epoxy for a pourable aggregate extension, which yields approximately 500 cubic inches. Use 20 – 60 US Sieve Mesh, aggregate should be round or tending toward round for best flowability.
- For troweling or patching use a flooring mortar tri-blended, with the larger aggregate being angular in shape.
- Broadcast 100 US Sieve Mesh aggregate that has been washed, dried, and bagged on patches or mortar repairs, to minimize tracking of uncured material if accidentally stepped on.

Note: ChemCo Systems can recommend pre-coated aggregate when it is required for safety reasons.

SAFETY

This bulletin does not accompany the product when sold. For hazard warnings, safe handling, and first aid instructions, CAREFULLY READ THE SAFETY DATA SHEETS AND CONTAINER WARNING LABELS.

Part A: Liquid epoxy resin, HMIS Health Hazard Rating- 2 (Moderate Hazard). Warning! Causes eye and skin irritation. May cause an allergic skin reaction. Harmful if swallowed. Avoid contact with eyes, skin, and clothing. Wash thoroughly after handling. Avoid prolonged or repeated contact with skin.

Part B: Liquid epoxy hardener, HMIS Health Hazard Rating- 3 (Serious Hazard). Contains alkaline amines. Danger! Causes severe eye and skin burns. May cause allergic skin and respiratory reactions. Corrosive, do not get in eyes or skin or on clothing. Avoid breathing vapor. Keep container closed. Use only with adequate ventilation. Wash thoroughly after handling. Keep away from heat and open flame.

CLEAN-UP / DISPOSAL

All tools and equipment must be cleaned before the mixed material cures. Cleaning can be facilitated with a solvent such as acetone or heavy-duty detergents. Cured material may be removed from equipment and tools by soaking in an epoxy stripper.

TECHNICAL SUPPORT

Additional information, technical assistance, and management services are also available from a ChemCo Systems Technical Consultant at sales@chemcosystems.com or 650-261-3790.

The properties listed in this bulletin are typical and descriptive of the product and should not be used for specification purposes. For specification preparation, reference the specification of this product available from ChemCo Systems.

CCS™ QUIKPRIME™

COATING – STRUCTURAL EPOXY ADHESIVE PRIMER FOR
POLYMER COATING & FLOORING SYSTEMS

TECHNICAL DATA SHEET FOR PROFESSIONAL CONTRACTOR USE ONLY



PROJECT NOTES



Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with ChemCo Systems materials or have undergone training in application of ChemCo Systems materials. Published technical data and instructions are subject to change without notice. Contact your local ChemCo Systems representative or visit our website for current technical data, instructions, and project specific recommendations.

ChemCo Systems warrants its products to be free of manufacturing defects and that they will meet ChemCo Systems' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by ChemCo Systems of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. ChemCo Systems shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. ChemCo Systems shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. ChemCo Systems reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and ChemCo Systems makes no claim that these tests or any other tests accurately represent all environments. ChemCo Systems is not responsible for typographical errors. © 2024 ChemCo Systems. All rights reserved. Revision 20240305.JC CPT 141 CCS-QUIKPRIME