CCS™ GROUT II

FLEXIBLE HYDROPHOBIC POLYURETHANE FOAM

TECHNICAL DATA SHEET FOR PROFESSIONAL CONTRACTOR USE ONLY

DESCRIPTION

CCS™ Grout II is a two-component, moisture-cured polymer that reacts with water to form a tough, flexible, closed cell hydrophobic polyurethane foam. It is designed to fill large voids and cracks in stone or concrete.

FEATURES

- Forms A Flexible Gasket or Plug
- Prevents Water Infiltration

SURFACE PREPARATION

Substrate surfaces must be dry, sound, and free of all bond-inhibiting substances. Prepare surfaces according to ASTM D 4259 or ACI 503R and ChemCo Systems' specific recommendations. Cleaned concrete surfaces should have a minimum strength of 250 psi (1.38 MPa) in direct tension. Cleaned asphalt surfaces should have a minimum strength of 100 psi (0.68 MPa) at $73^{\circ}F \pm 4^{\circ}F$ ($23^{\circ}C \pm 1^{\circ}C$). in direct tension. Steel surfaces should be cleaned to "white metal" according to SSPC SP 5.

INSTALLING

For filling control joints, wire slots, and saw cuts, transfer mixed material to a pour can with a spout sized for the joint to be filled. Fill the joint in a single direction. For a filled surface flush with the surrounding substrate, overfill slightly the joint until a crown of material is formed

For narrow or deep joints, filling in two steps with the bulk of the material placed in the first step allows trapped air and settlement to occur for a more uniform installation. Following the initial cure, excess material (high spots) may be removed by warming with a hot air stream (heat gun) and cutting with a sharp blade.

CLEAN UP

Excess mixed product is best removed from the work area and tools before it hardens. The use of rags and solvents such as acetone or heavy-duty detergents facilitates cleaning. Cured product may be removed from tools by soaking in an epoxy stripper.

PACKAGING & COLORS

- Standard package sizes of 5 1/2-gallon kit:one 5 gallon (18.9 liters) pail of Side-A and and one 1/2 gallon (0.95 liters) can of Side-B Catalyst.
- Standard color is pale yellow.

SHELF LIFE

One year minimum in unopened, original containers when stored



between 60 and 95°F (15-35°C) in a dry place away from sunlight. Remixing of components may be required upon long-term storage.

TECHNICAL DATA

PHYSICAL PROPERTIES	TEST METHOD	VALUE
Mix Ratio, A:B		10:1 by volume
Color		Part-A: Pale Yellow Part-B: Clear
Density	ASTM D1638	Part-A 9.04 lbs Part-B: 8.39 lbs
Viscosity	ASTM D1638	Part-A: 500 <u>+</u> 150 cp Part-B: 50 <u>+</u> 20 cp
Flash Point	ASTM D93	Part-A : 200°F (93°C) Part-B : 200°F (93°C)
Solubility in Water		not soluable
Expansion		800-1000%
Induction Time (approximately)		30-40 seconds
Gel Time (approximately)		2-3 minutes
Corrosiveness		Non Corrosive



Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with ChemCo Systems materials or have undergone training in application of ChemCo Systems materials. Published technical data and instructions are subject to change without notice. Contact your local ChemCo Systems representative or visit our website for current technical data, instructions, and project specific recommendations.

ChemCo Systems warrants its products to be free of manufacturing defects and that they will meet ChemCo Systems' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by ChemCo Systems of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. ChemCo Systems shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. ChemCo Systems shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. ChemCo Systems reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own information and test, not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and ChemCo Systems and sets no claim that these tests or any other tests accurately represent all environments. ChemCo Systems is not responsible for typographical errors. © 2021 ChemCo Systems. All rights reserved. Revision 20210323.AG